

P-601 Polyester Prepregs

Park's P-601 is a flame retardant polyester resin system with good electrical and structural properties. Designed for woven-roving applications.

Key Features & Benefits

- Meets MIL-R-7575 Grade A, Class 3 requirements
- Non-styrenated / Low VOC
- Good electrical and structural properties
- Flame retardant
- Good alternative for wet lay-up processing

Product Forms

- Available on a variety of reinforcements
- Solution coated fabrics up to 60 inches wide
- Compatible with Autoclave, Vacuum Bag/Oven or Press Molding processes

Vacuum/Oven Cure Cycle

- Apply 610 mmHg vacuum (minimum) for 1 hour before beginning heat cycle
- Heat at 1–2°C/min from room temperature to 65°C
- Cure product at 65°C for 30 minutes
- Ramp heat at 1–2°C/min to 121°C
- Cure product at 121°C for 90 minutes
- Cool to 65°C at no more than 5°C/min prior to releasing autoclave pressure

Note: These guidelines are provided to assist Park material users with general recommendations for successful processing. The recommendations are for general review purposes only and process adjustments may be required to achieve optimum results in your specific manufacturing environment.

Applications / Qualifications

- Radomes
- Large Structures

For Information about Park's materials:

Newton, KS +1.316.283.6500
info@parkaerospace.com
www.parkaerospace.com

P-601 Polyester Prepregs

Prepreg Physical Properties

Reinforcement	18 oz Fiberglass Woven Roving
Fabric Area Weight (gsm)	610
Prepreg Resin Content (%)	34 - 39
Resin Flow (124°C, 103 kPa) (%)	8 – 17
Volatiles (121°C, 8 min) (%)	3.0 (max)
Gel Time (sec)	70 – 120

Laminate Physical Properties

Reinforcement	18 oz Fiberglass Woven Roving
Dielectric Constant (Dk) @ 9.375 GHz	4.4
Loss Tangent (Df) @ 9.375 GHz	0.02
Hardness (Barcol)	64
Specific Gravity	
Tensile Strength, 0° (MPa) 24°C Dry 121°C Dry ASTM-D-638 Type 1	262
Tensile Modulus, 0° (GPa) 24°C Dry 121°C Dry ASTM-D-638 Type 1	20.7
Compressive Strength (MPa) 24°C Dry 121°C Dry ASTM-D-695	
Compressive Modulus (GPa) 24°C Dry 121°C Dry ASTM-D-695	20.7
Flexural Strength (MPa) 24°C Dry 121°C Dry ASTM-D-790	303
Flexural Modulus (GPa) 24°C Dry 121°C Dry ASTM-D-790	11.1

Aerospace Composite Materials

Prepreg Storage Life

Out Life: 21 days @ 24°C

Shelf Life: 6 months @ -18°C

All test data provided are typical values and not intended to be specification values. For review of critical specification tolerances, please contact a company representative directly.

Park Aerospace Corp. reserves the right to make changes without notice to any products described herein. Park does not assume any liability arising out of the application or use of any product described herein; and it does not grant any license under its patent or other rights or any such rights of others. Park also disclaims all warranties whether expressed, implied or statutory, including implied warranties of merchantability or fitness for a particular purpose.

Aeroglide®, ALPHA STRUT™, CoreFix®, Easycure E-710®, Electroglide®, Electrovue™, Peelcote™, Powerbond™, RadarWave™, SIGMA STRUT™ and Tin City Aircraft WorksSM are trademarks or servicemarks of Park Aerospace Corp.

