

P-650M Polyester Prepregs

Park's P-650M is a polyester resin system suitable for coating on any MIL-C-9084. P-650M has good electrical and mechanical properties and has been used in a wide variety of applications, including embossing die fabrication and aircraft structural parts

Key Features & Benefits

- Meets requirements of MIL-R-7575C, grades A and B
- Good electrical and structural properties
- Excellent retention of mechanical properties at elevated temperatures

Product Forms

- Available on a wide variety of reinforcement
- Solution coated fabrics up to 60 inches wide
- Compatible with Autoclave, Vacuum Bag/Oven or Press Molding processes

Applications / Qualifications

- Embossing die fabrication
- Aircraft structural parts
- Electrical Insulation

For Information about Park's materials:

Newton, KS +1.316.283.6500

info@parkaerospace.com

www.parkaerospace.com



P-650M Polyester Prepregs

Prepreg Physical Properties

Reinforcement	7781 E-glass
Fabric Area Weight (gsm)	300
Prepreg Resin Content (%)	42 – 48
Volatiles (220°F, 8 min) (%)	2.0 max
Gel Time (sec)	45

Processing Guidelines

Prepreg Storage Life

- Out Life: 30 days @ 75°F
- Shelf Life: 8 months @ 40°F
- 12 months @ 0°F

Note: The following guidelines are provided to assist Park material users with general recommendations for successful processing. The recommendations are for general review purposes only and process adjustments may be required to achieve optimum results in your specific manufacturing environment.

Press Cure Cycle

- Apply 100 psi pressure
- Cure for 45 minutes at 300°F

Laminate Physical Properties

Reinforcement	7781 E-glass
Hardness (Barcol)	71
Specific Gravity	1.89
Dielectric Constant (Dk)	
8.6 GHz Dry	3.56
13.6 GHz Dry	3.49
8.6 GHz Wet	3.61
13.6 GHz Wet	3.52
Loss Tangent (Df)	
8.6 GHz Dry	0.011
13.6 GHz Dry	0.009
8.6 GHz Wet	0.040
13.6 GHz Wet	0.020

All test data provided are typical values and not intended to be specification values. For review of critical specification tolerances, please contact a Park representative directly. Park reserves the right to change these typical values as a natural process of refining our testing equipment and techniques.



P-650M Polyester Prepregs

Laminate Physical Properties

Reinforcement	7781 E-glass
Tensile Strength, 0° (Ksi) 75°F Dry 250°F Dry ASTM-D-638 Type 1	52 36
Tensile Modulus, 0° (Msi) 75°F Dry 160°F Dry ASTM-D-638 Type 1	3.1 2.6
Compressive Strength (Ksi) 75°F Dry 160°F Dry ASTM-D-695	47 37
Compressive Modulus (Msi) 75°F Dry 160°F Dry ASTM-D-695	3.5 3.0
Flexural Strength (Ksi) 75°F Dry 160°F Dry ASTM-D-790	72 52
Flexural Modulus (Msi) 75°F Dry 160°F Dry ASTM-D-790	3.7 2.6

All test data provided are typical values and not intended to be specification values. For review of critical specification tolerances, please contact a company representative directly.

Park Aerospace Corp. reserves the right to make changes without notice to any products described herein. Park does not assume any liability arising out of the application or use of any product described herein; and it does not grant any license under its patent or other rights or any such rights of others. Park also disclaims all warranties whether expressed, implied or statutory, including implied warranties of merchantability or fitness for a particular purpose.

Aeroglide®, ALPHA STRUT™, CoreFix®, Easycure E-710®, Electroglide®, Electrovue™, Peelcote™, Powerbond™, RadarWave™, SIGMA STRUT™ and Tin City Aircraft Works™ are trademarks or servicemarks of Park Aerospace Corp.

